

	Deg. Celcius		Deg. Celcius			Degree Fahrenheit		
	Low	High	Low	High	Range	Low	High	Range
Styrene-Butadiene Rubber (SBR)	-44	94	-45	95	140	-49	203	252
Polyurethane Rubber (AU, EU)	-35	85	-35	85	120	-31	185	216
Butyl Rubber (IIR)	-63	106	-65	105	170	-85	221	306
Low Temperature Nitrile Rubber (NBR)	-50	113	-50	115	165	-58	239	297
Hydrogenated Nitrile Rubber (HNBR)	-25	150	-25	150	175	-13	302	315
High Temperature Nitrile Rubber (NBR)	-31	138	-30	140	170	-22	284	306
Chloprene Rubber (CR)	-44	102	-45	100	145	-49	212	261
Polyacrylate Rubber (ACM)	-15	152	-15	150	165	5	302	297
Etylene-Propylene-Diene Rubber (EPM, EPDM)	-44	152	-45	150	195	-49	302	351
Flurosilicone-Rubber (FMQ,FVMQ)	-52	176	-50	175	225	-58	347	405
TFE/Propylene Rubber (FEPM)	0	232	0	230	230	32	446	414
Flurocarbon Rubber (FKM)	-18	202	-20	200	220	-4	392	396
Perfluorinated Elastomer (FFKM)	-10	250	-10	250	260	14	482	468
Silicone Rubber (VMQ, MQ, Q, PVMQ)	-52	208	-50	210	260	-58	410	468
Natural Rubber (NR)	-50	100	-50	100	150	-58	212	270
Ethylene Acrylate Rubber (AEM)	-40	160	-40	160	200	-40	320	360
Butadiene Rubber (BR)	-70	70	-70	70	140	-94	158	252
Carboxylated Nitrile Rubber (XNBR)	-28	150	-30	150	180	-22	302	324
Chlorosulfonated Polyethylene Rubber (Hypalon, CSM)	-28	121	-30	120	150	-22	248	270
Epichlorohydrin (CO), ECO)	-48	135	-50	135	185	-58	275	333
Chlorobutyl Rubber (CIIR)	-50	126	-50	125	175	-58	257	315
Tetrafluoroethylene-Propylene (AFLAS)	-40	260	-40	260	300	-40	500	540
Polysulfide Rubber (PSR)	-54	107	-55	105	160	-67	221	288